

White Label Technology

Bondchem WR18 is produced from our latest non-hazardous technology incorporating a bespoke group of high purity raw materials. This unique future-proof technology ensures that the product label requires no hazard symbols or risk and safety phrases, and enables the product to comply with even the most stringent health and safety requirements.

Product Description

Bondchem WR18 is a high strength medium viscosity retaining compound, designed to bond close fitting metal surfaces with an ultimate structural strength. **WR18** specializes in bonding cylindrical fitting parts, and maintains an unfaltering bond under all levels of cyclic load stress distribution.

Typical Applications

Bondchem WR18 can be used in a wide variety of applications, especially interference or press fit parts including

- High strength retention of bearings
- Locking of keys and splines
- Bonding rotors, bushes and sleeves to shafts
- Securing loose or worn parts

Instructions For Use

1. For best results clean all surfaces with a cleaning solvent and allow to dry.
2. If the metal is inactive or the gap >0.2mm, apply **Bondchem A249 activator** to increase cure speed.
3. Apply the adhesive to both the inside of the collar, and the leading edge of the pin, and assemble parts with a rotational motion, ensuring a high surface coverage.
4. Allow parts to cure to handling strength.

Properties of Uncured Material

Resin	Dimethacrylate
Colour	Green
Viscosity @ 20°C	
Brookfield Sp 5 @ 20rpm	2000 – 3000 cps

Performance of Cured Material

Fixture Time Stainless Steel	8-15 min @ 22°C
Fixture Time with A249	<3 Minutes
Full Cure Time	24 hours @ 20°C
Gap Fill (Diametrical)	Up to 0.25mm
Strength Break Loose M10	57 Nm
Strength Prevailling M10	22 Nm
Temperature Range	-50°C to 150°C

Packaging

Bondchem AW18 is available in 10ml, 50ml, 250ml LDPE bottles. In addition, we can offer automated dispensing lines for the bulk dispensing of this material.

Storage & Shelflife

Bondchem AW18 should be stored in a cool dry area, out of direct sunlight. Stored correctly, this grade can offer a 12 month shelf life from manufacture.

Health and Safety in Use

Bondchem M130 is a methyl methacrylate and should not be used without consulting the MSDS, which contains full information regarding the use of this product, including Transport, Disposal, Toxicological, Exposure Controls, Accidental Release and First Aid measures essential to the safe use of this product.