

**PVAc Dowelling Glue****114.60**

**Application:** For dowel glueing of soft or hard-textured wood and particleboard on dowelling machines.

**Characteristics / Directions for Use:** Low viscosity, joint filling, tough-elastic glue film.

**We recommend that all materials coming into contact with the glue are made of high-quality stainless steel (German standard V2A or better) or of inert plastics, e.g. Teflon, PP, polyamide. Avoid contact with other metals like zinc, brass, copper or aluminium. For more information, contact the equipment manufacturer or our technical service.**

For pressurized containers and high-pressure pumps with nozzle applicators.  
Avoid contact with iron; tanniferous wood may discolour.

Min. temp. for materials, glue and room air [°C]: 15 (not identical with minimum film-forming temperature).

Crust formation at the nozzle is avoided by a special formulation to facilitate startup after down times.

<b>Technical Data:</b>	Viscosity [mPas]:	approx. 350 (Brookfield)
	Solids [%]:	approx. 39
	Density [g/cm <sup>3</sup> ]:	approx. 1.06
	pH value:	approx. 4.5
	Min. film-forming temperature [°C]:	approx. 5
	Appearance of the dry glue film:	colourless translucent

**Cleaning:** Machines and equipment may be cleaned after use with warm or cold water, using Jowat® Cleaner Concentrate 192.40.

**Storage:** In properly closed original containers, cool and dry (15 – 25 °C). Best-before date, please refer to label on the packaging unit. Protect against frost!

**Packaging:** Type of packaging and units upon request.

**Remarks:** For further information concerning handling, transport and disposal, please refer to the Safety Data Sheet.  
Our information on this data sheet is based on test results from our laboratories as well as on experience gained in the field by our customers. It can, however, not cover all parameters for each specific application and is therefore not binding for us. The information given in this leaflet represents neither a performance guarantee nor a guarantee of properties, nature, condition, state or quality. No liability may be derived from these indications nor from the recommendations made by our free technical advisory service

**01/16** All data indicated are characteristics represented as average values. Our technical data sheets are constantly revised to represent the latest state of technology. This edition is replacing all previous ones, and is valid on the date of compilation.  
**Please refer to last page for additional information.**

**Jowat**  
Klebstoffe 

**Jowat SE** · Ernst-Hilker-Straße 10-14 · 32758 Detmold · Germany · Phone: +49 (0)5231 749-0 · Fax: +49 (0)5231 749-105 · info@jowat.de · www.jowat.de

## **Jowat Information**

Glueing as one of the most efficient methods of bonding is constantly gaining importance and expanding into new areas of application. At the same time, the number of substrates to be bonded is also growing at an unprecedented rate. New methods and equipment to process adhesives are developed.

The in-house R & D departments of Jowat are responding with intensive efforts to keep pace with these constant changes. A highly qualified team of chemists and engineers is using the latest techniques and brightest ideas to provide the utmost in advice our customers and to make sure that they get the adhesive which meets their needs.

Our information is based on test results from our laboratories as well as on experience gained in the field by our customers. This advice, however, cannot cover all eventualities for each specific application and as such is not binding for us. Please, contact our technical service department in each case to find out what the actual technical state of development for the respective product is, and request the latest data sheet. Any use of our product without this precautionary measure would be your sole responsibility.

The processing company itself must therefore test the adhesives manufactured by us for suitability in each individual case. This applies to the first use of a sample as well as to modifications during an ongoing production.

We are therefore requesting all our new customers to test our adhesives for suitability on original parts at conditions equal to normal processing conditions. The bond has then to be subjected to the actual stress which it would undergo when in use and has to be assessed. This test is absolutely necessary.

Customers who undertake modifications during a running production are requested to pass this information on to us. Please notify us when machines are set to new parameters as well as when the substrates to be bonded are changed. Only then will Jowat be able to provide our most up-to-date information to the processor using our adhesives.

The information given in this leaflet is based on practical experience and on results of tests in our laboratory, and does in no way constitute any guarantee of properties. No liability may be derived from these indications nor from the recommendations made by our technical advisory service.