

Technical Data Sheet

SX Premium Superglue Cyanoacrylate Adhesive



Product Description

An ethyl cyanoacrylate adhesive which has been developed for the bonding of most rubbers and plastics such as PVCu. This one component, solvent free adhesive bonds rapidly at room temperature and is economical to use.

Packaging: 20gm & 50gm bottles (packed 1 x 25). Available in Medium & High Viscosity.

Benefits

- Bonds most rubbers and plastics such as PVCu. Bonds rapidly at room temperature.

Uses

Can be used to bond trims and caps on PVCu windows but can also bond most plastics, wood, plywood, leather, cork, most rubber, rubber foams, filled rubbers, ceramics and most metals. Can be used in conjunction with SX Activator to achieve an even faster bond. SX Superglue De-bonder can be used to free most accidentally bonded items.

Directions of Use

Apply a small amount to one surface and assemble parts, holding for approximately 10-60 seconds. Cure speed is rapid so take care when aligning. Maximum strength is achieved in 24-48 hours.

Additional information

Base		Ethyl Cyanoacrylate
Viscosity	25°C High viscosity	1000-1500

Surface Preparations and Finishing

Ensure surfaces are clean and dry. Adhesion tests prior to application are recommended.

Cleaning

Issue 7/29.04.16/0268.4.C

Colour(s)

- Medium viscosity: clear / High viscosity: transparent, colourless to yellowish

Shelf Life

Shelflife of 12 months after production date. Below +5°C - 12-18 months. Store in a cool, dry location. Best when stored at +2°C - +8°C. Temperatures less than +2°C can adversely affect product properties. Do not freeze. Keep container tightly closed until ready for use.

Health & Safety

Safety data sheet (MSDS) must be read and understood before use of product. These are available on request and via the Siroflex website on the product pages.

Warranty & Guarantee

Siroflex warrants that its product complies, within its shelf life, to its specification.

Disclaimer

All information in this document and in all our other publications (including electronic ones) is based on our current knowledge and experience and is the exclusive (intellectual) property of Siroflex Limited. No part of this document may be copied, shown to third parties, reproduced, communicated to the public or used in any other way without Siroflex Ltd's written consent. The technical information in this document serves as an indication and is non-exhaustive. Siroflex Ltd is not liable for any damage, either direct or indirect, due to (editorial) errors, incompleteness and/or incorrectness of this document. This includes, but is not limited to, incompleteness and/or incorrectness due to technological changes or any research conducted between the date of publication of this document and the date on which the product is acquired. Siroflex Ltd reserves the right to amend the wording of this document. Siroflex Ltd cannot be held liable for any damage, either direct or indirect, due to the use of the product depicted in this document. The user must read and understand the information in this document and other documents relating to the products prior to the use of the product. The user is responsible for performing all the requisite tests to make sure that the product is suitable for its intended use. We have no influence in what way the product is applied and/or any circumstances relating to events occurring during storage or transport and therefore we do not accept any liability for damage. All deliveries are made exclusively in accordance with our Terms & Conditions of sale.

